Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 14/03/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 09-03-20

Customer ID : Retaining Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 14/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	151.72 X 149.94 X 151.08	22749	**8.330**	540.3	23.7	22.9
2	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	150.55 X 150.40 X 151.35	22643	**8.725**	509.8	22.5	
3	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	150.15 X 149.36 X 149.88	22426	**8.601**	503.4	22.4	

FOR CIVIL Pro.

CIVIL Pro Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 04/04/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 09-03-20

Customer ID : Retaining Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/04/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	150.74 X 151.49 X 151.45	22836	**8.770**	620.2	27.2	27.6
2	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	149.95 X 149.80 X 150.85	22461	**8.832**	603.6	26.9	
3	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	150.08 X 149.23 X 149.71	22397	**8.853**	643.8	28.7	

FOR CIVIL Pro.

CIVIL Pro Sig. Date ORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 18/05/2020

Lab ID : **CP-2020-06-17-04**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	18/05/2020	150.28 X 150.85 X 149.91	22669	**8.330**	538.3	23.7	22.9
2	Copping Concrete	M25	11/05/2020	18/05/2020	150.19 X 151.51 X 149.87	22756	**8.725**	514.5	22.6	
3	Copping Concrete	M25	11/05/2020	18/05/2020	149.50 X 150.15 X 151.45	22448	**8.601**	498.4	22.2	

CIVIL Pro Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 08/06/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 13-05-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/06/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M25	11/05/2020	08/06/2020	149.60 X 151.05 X 151.96	22597	**8.770**	627.7	27.8	27.6
2	Copping Concrete	M25	11/05/2020	08/06/2020	151.78 X 151.35 X 149.71	22973	**8.832**	608.5	26.5	
3	Copping Concrete	M25	11/05/2020	08/06/2020	150.18 X 150.01 X 151.75	22529	**8.853**	643.1	28.5	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04**

Date: 10/03/2020

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 05-03-20

Customer ID : Retaining Wall Base Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Base Concrete	M25	03/03/2020	10/03/2020	150.71 X 151.36 X 151.54	22812	**8.330**	533.7	23.4	22.9
2	Retaining Wall Base Concrete	M25	03/03/2020	10/03/2020	149.16 X 151.04 X 151.43	22530	**8.725**	510.2	22.6	
3	Retaining Wall Base Concrete	M25	03/03/2020	10/03/2020	150.44 X 151.99 X 151.98	22864	**8.601**	519.4	22.7	

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 31/03/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 05-03-20

Customer ID : Retaining Wall Base Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Base Concrete	M25	03/03/2020	31/03/2020	150.05 X 150.73 X 150.29	22616	**8.770**	621.7	27.5	27.5
2	Retaining Wall Base Concrete	M25	03/03/2020	31/03/2020	149.86 X 149.16 X 149.15	22353	**8.832**	587.3	26.3	
3	Retaining Wall Base Concrete	M25	03/03/2020	31/03/2020	150.35 X 149.06 X 149.19	22411	**8.853**	644.6	28.8	

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 14/03/2020

Lab ID	:	**CP-2020-06-17-04**
Project Name	:	Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03
Agency	:	Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/158/19-20
Date of Receipt	:	09-03-20
Customer ID	:	Retaining Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	14/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	151.75 X 151.40 X 150.74	22974	**8.330**	548.3	23.9	22.6
2	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	151.86 X 149.44 X 149.29	22694	**8.725**	499.8	22.0	
3	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	151.05 X 151.57 X 150.31	22895	**8.601**	504.7	22.0	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro

R KARTHIK RECHAN
Authorized Signator
Quality Manage

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 04/04/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 09-03-20

Customer ID : Retaining Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/04/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	149.62 X 149.43 X 149.96	22358	**8.770**	619.6	27.7	27.7
2	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	150.63 X 151.20 X 150.66	22777	**8.832**	605.9	26.6	
3	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	149.95 X 151.19 X 149.69	22672	**8.853**	652.0	28.8	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 14/03/2020

Lab ID : **CP-2020-06-17-04**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 09-03-20

Customer ID : Retaining Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 14/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	149.70 X 149.68 X 151.14	22407	**8.330**	536.5	23.9	23.0
2	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	151.18 X 151.21 X 150.27	22859	**8.725**	509.6	22.3	
3	Retaining Wall Concrete	M25	07/03/2020	14/03/2020	149.72 X 149.49 X 149.95	22381	**8.601**	510.9	22.8	

FOR CIVIL Pr

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHA
Authorized Signato
Quality Manag

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 04/04/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 09-03-20

Customer ID : Retaining Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/04/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	150.17 X 150.58 X 151.16	22613	**8.770**	617.1	27.3	27.4
2	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	151.71 X 150.59 X 149.88	22845	**8.832**	612.8	26.8	
3	Retaining Wall Concrete	M25	07/03/2020	04/04/2020	149.82 X 151.77 X 149.44	22739	**8.853**	641.9	28.2	

CIVIL Pro Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 20/03/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 16-03-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 20/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	13/03/2020	20/03/2020	151.56 X 150.20 X 149.29	22765	**8.172**	431.5	19.0	18.5
2	PCC	M20	13/03/2020	20/03/2020	150.13 X 150.46 X 150.15	22588	**8.820**	417.6	18.5	
3	PCC	M20	13/03/2020	20/03/2020	151.11 X 149.81 X 150.04	22638	**8.166**	408.6	18.1	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 10/04/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 16-03-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/04/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	13/03/2020	10/04/2020	150.53 X 149.61 X 151.35	22521	**8.820**	519.8	23.1	22.8
2	PCC	M20	13/03/2020	10/04/2020	151.84 X 149.23 X 149.26	22660	**8.149**	503.9	22.2	
3	PCC	M20	13/03/2020	10/04/2020	150.16 X 150.97 X 149.75	22669	**8.790**	522.8	23.1	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 10/03/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 05-03-20

Customer ID : Retaining Wall Base Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Base Concrete	M25	03/03/2020	10/03/2020	150.47 X 150.35 X 150.59	22622	**8.330**	526.0	23.3	22.5
2	Retaining Wall Base Concrete	M25	03/03/2020	10/03/2020	150.94 X 151.28 X 151.28	22834	**8.725**	504.1	22.1	
3	Retaining Wall Base Concrete	M25	03/03/2020	10/03/2020	149.46 X 149.50 X 149.71	22344	**8.601**	492.9	22.1	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 31/03/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 05-03-20

Customer ID : Retaining Wall Base Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Base Concrete	M25	03/03/2020	31/03/2020	150.00 X 150.90 X 151.56	22635	**8.770**	626.3	27.7	27.4
2	Retaining Wall Base Concrete	M25	03/03/2020	31/03/2020	151.22 X 150.74 X 150.10	22794	**8.832**	595.0	26.1	
3	Retaining Wall Base Concrete	M25	03/03/2020	31/03/2020	149.19 X 149.24 X 151.54	22265	**8.853**	632.3	28.4	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 10/03/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 05-03-20

Customer ID : Retaining Wall Base Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Base Concrete	M25	03/03/2020	10/03/2020	149.31 X 149.32 X 151.90	22295	**8.330**	519.9	23.3	22.7
2	Retaining Wall Base Concrete	M25	03/03/2020	10/03/2020	150.22 X 149.82 X 151.72	22505	**8.725**	506.7	22.5	
3	Retaining Wall Base Concrete	M25	03/03/2020	10/03/2020	151.04 X 149.37 X 151.05	22562	**8.601**	503.9	22.3	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-06-17-04** **Date: 31/03/2020**

Project Name : Construction of Retaining Wall and Other Development Works to Marriage Community Hall Building at Chikkabettahalli in Ward No.03

Agency : Sri.H.V.Onkarappa, #27, Taralabalu Enclave, Near Police Station, Yelahanka, Bangalore-64.

Customer's Reference : EE(Project)/Ynk Zone/WO/158/19-20

Date of Receipt : 05-03-20

Customer ID : Retaining Wall Base Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/03/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Retaining Wall Base Concrete	M25	03/03/2020	31/03/2020	151.71 X 151.14 X 149.91	22930	**8.770**	633.9	27.6	27.6
2	Retaining Wall Base Concrete	M25	03/03/2020	31/03/2020	150.59 X 151.55 X 150.00	22822	**8.832**	598.2	26.2	
3	Retaining Wall Base Concrete	M25	03/03/2020	31/03/2020	150.86 X 150.83 X 149.12	22755	**8.853**	657.3	28.9	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |